

Material	Process Melt Temp. (°F)	Mold Temp.	Temp (°F)	Hours
ABS High Impact	440-510	90-180	190	4
ABS High Heat	510-540	140-180	190	4
ABS Med Impact	440-510	90-180	190	4
Acetal	380-420	140-220	Homo 200 Co 210	1.5
Acrylic Gen Purpose	420-485	120-180	180	1.5
Acrylic High Heat	420-485	120-180	180	2.5
Acrylic High Impact	420-485	120-180	180	2.5
Nylon 6/6	500-560	120-180	180	4
Nylon 6	470-530	100-180	180	4
Nylon 6/10	460-510	100-180	180	4
Nylon 12	400-450	80-120	180	4
Polycarbonate Med Vis.	540-570	160-200	250	3.5
PET - Bottle	520-560	60-120	340	5
PBT	460-490		260	2.5
PBT 30% Glass Filled	460-490			
Polyetherimide	680-720	220-330	310	4
Polyethylene LD	340-440	50-100		
Polyethylene HD	390-490	50-150		
PPO	480-580	150-220	210	2.5
Polypropylene	420-520	60-150		
Polystyrene Gen Purpose	360-460	50-120		
Polystyrene High Heat	400-480	50-120		
Polystyrene High Impact	400-480	50-120		
PVC Rigid	320-420	50-120		
PVC Semi Rigid	320-420	50-120		
PVC Flexible	320-420	50-120		
SAN	400-500	70-120	180	3

Contact Us: 800-920-8033 or Info@GP-Materials.com

This Injection Molding Processing Guide is offered as an informational service to customers of General Polymers Thermoplastic Materials and users of products made from these plastics. While General Polymers Thermoplastic Materials has used reasonable efforts to provide accurate information in this publication, General Polymers Thermoplastic Materials expressly disclaims any liability for damages, costs or losses resulting from reliance on the contents of this Injection Molding Processing Guide. It is the responsibility of the product manufacturer to determine the suitability of any design or product for its intended purpose.